

High molecular weight general purpose polystyrene combining high heat resistance and good mechanical strength. N 3380 belongs to the third generation of Edistir®GPPS.

Suitable for direct gassing extrusion, biaxially oriented film and sheet, glass clear sheet and panels.

Also used in injection moulding of medium wall-thickness transparent parts.

Thanks to N 3380, injected items will be brighter and neutral coloured in line with more sophisticated market needs.

The new colour will not be noticeable in covered applications.

Designation: Thermoplastics ISO 1622-PS,G,105-03.

## Applications

Suitable for foamed packaging trays, clear panels for shower cubicles, insulation boards (XPS), OPS for labels and packaging, clear moulded fridge components, petri dishes and technical parts.

## Typical processing data

Extrusion:

- melt temperature 210-240°C

Injection moulding:

predrying normally not required

- melt temperature 220-270°C  
suggested temperature around 240°C
- mould temperature 20-60°C

## General information

This product in the natural version complies by composition with the requirements of the main Regulations for plastic materials intended to come into contact with food, including Regulation (EU) No 10/2011 and following amendments.



versalis

info.styrenics@versalis.eni.com

Technical Data Sheet

**Edistir®N 3380**

Polystyrene

Property	Test Conditions	Test method	Units	Values
<b>General</b>				
Water absorption	24h - 23°C	ISO 62	%	<0,1
Bulk density	-	ISO 60	g/cm <sup>3</sup>	0,65
<b>Rheological</b>				
Melt flow rate	200°C - 5kg	ISO 1133	g/10'	2
<b>Mechanical</b>				
Tensile strain at break	5 mm/min	ISO 527	%	2,5
Tensile stress at break	5 mm/min	ISO 527	MPa	49
Flexural strength	2 mm/min	ISO 178	MPa	91
Rockwell hardness	L/M	ISO 2039/2	-	M80
Tensile modulus	1 mm/min	ISO 527	MPa	3350
Izod impact strength, notched	+23°C - 4mm	ISO 180/1A	kJm <sup>2</sup>	1,9
Izod impact strength, notched	-30°C - 4mm	ISO 180/1A	kJm <sup>2</sup>	1,7
<b>Thermal</b>				
Coefficient of linear thermal expansion	-	ASTM D 696	10 <sup>-5</sup> /°C	7
Thermal conductivity	-	ISO 8302	W/(K.m)	0,17
Moulding shrinkage	-	ISO 294/4	%	03 - 0,6
Deflection temperature under load (annealed)	1,82 MPa - 120°C/h	ASTM D 648	°C	95
Vicat softening temperature	50 N - 50°C/h	ISO 306/B	°C	101
Vicat softening temperature	10 N - 50°C/h	ISO 306/A	°C	106
<b>Flammability</b>				
Flame behaviour	1,5 mm	UL 94	cl.	HB
Glow wire test (GWT)	1,6 mm	IEC 60695-2-1	°C	650
<b>Electrical</b>				
Dielectric constant (relative permittivity)	50 Hz	IEC 60250	-	2,5
Dissipation factor	50 Hz	IEC 60250	-	0,0002
Comparative tracking index (CTI)	Sol. A	IEC 60112	-	425
Surface resistivity	-	IEC 60093	10 <sup>15</sup> ohm	>1,5
Volume resistivity	-	IEC 60093	10 <sup>15</sup> ohm.cm	>7
Dielectric strength	-	IEC 60243	kV/mm	70

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate but no warranty or guarantee, expressed or implied, is made nor is any liability accepted.

Versalis is available to provide the guaranteed values for each product on demand.