

RIBLENE®

FC 39 F

LDPE

Low density polyethylene

Riblene FC 39 F is a high molecular weight low density polyethylene (LDPE) suitable for blown film extrusion. Riblene FC 39 F is characterised by a high melt strength leading to a good bubble stability during extrusion.

Films manufactured by Riblene FC 39 F are easily heat shrinkable and characterised by high rigidity, good mechanical and optical properties.

Main Applications

Riblene FC 39 F is recommended for the production of medium rigidity shrink film characterized by good clarity and gloss.

Main Properties

Resin Properties	Value	Unit	Test Method
Melt Flow Rate (190 °C/2.16 kg)	0.25	g/10min	ISO 1133
Melt Flow Rate (190 °C/5 kg)	-	g/10min	ISO 1133
Melt Flow Rate (190 °C/21.6 kg)	-	g/10min	ISO 1133
Density	0.923	g/cm ³	ISO 1183
Melting Point	113	°C	Internal method
Brittleness temperature	<- 75	°C	ASTM D 746
Vicat softening point (1 kg)	93	°C	ISO 306/A

Film Properties *	Value	Unit	Test Method
Tensile stress at yield MD	10	MPa	ISO 527-3
Tensile stress at yield TD	10	MPa	ISO 527-3
Tensile stress at break MD	27	MPa	ISO 527-3
Tensile stress at break TD	25	MPa	ISO 527-3
Elongation at break MD	400	%	ISO 527-3
Elongation at break TD	600	%	ISO 527-3
1% Secant modulus MD	160	MPa	ISO 527-3
1% Secant modulus TD	180	MPa	ISO 527-3
Elmendorf tear resistance MD	25	N/mm	ISO 6383-2
Elmendorf tear resistance TD	40	N/mm	ISO 6383-2
Impact resistance F50 (Dart Drop Test)	320	g	ISO 7765-1/A
Dynamic coefficient of friction (COF)	> 0.5	-	ISO 8295
Haze	9	%	ISO 14782
Gloss, 45°	60	%	ASTM D 2457
Recommended film thickness	40 ÷ 150	micron	-

(*) Typical value for a film extruded with BUR 1:3, thickness 70 µm. Actual properties are typical and may vary depending upon operating conditions and additive package.

Riblene® is a registered trademark of versalis

Processing notes

Riblene FC 39 F is easily processable using blown film technology. Melt temperature should be between 180°C and 220°C. Recommended thickness: 40 - 150 µm.

Storage and Handling

Riblene FC 39 F is supplied in pellet form. This material may readily be conveyed and bulk fed through equipment designed for conventional pelletised polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practised throughout your facility.

The product should be stored in dry conditions at temperatures below 50°C and protected from sunlight. Improper storage can initiate degradation which results in odour generation, colour changes and can have negative effects on the physical properties of the product. Before using this product it is recommended to read and understand the relevant Safety Data Sheet.

Availability

Contact the versalis sales office nearest to you regarding availability and your specific application requirements.

Food Contact Status

Riblene FC 39 F complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

TECHNICAL SERVICE

Center and South Europe and Americas

Versalis S.p.A.

Head Office
Piazza Boldrini, 1
20097 San Donato Milanese (MI) - Italy
tel. +39 02 52032087 + 39 02 52042984
tel. +39 02 52042005 + 39 02 52032318

Mantova
Via Taliercio 14 - 46100 Mantova (MN) - Italy
tel. +39 0376 305520 +39 0376 305741

North Europe and ROW

Versalis S.p.A.

Piazza Boldrini, 1
20097 San Donato Milanese (MI) - Italy
tel. +39 02 25032190

4531 Route des Dunes - CS 20060 Mardyck 59279
Dunkerque - France
tel. +33 3 28 23 55 16

Duesseldorfer Str. 13
65760 Eschborn – Deutschland
tel +49 6196 492 249

IMPORTANT: please consult the relevant safety data sheet for more detailed information. The information and data presented herein are to the best of our knowledge true and accurate but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information and data. Versalis is available to provide the guaranteed values for each product on demand. DISCLAIMER: it is the sole responsibility of the end-user to determine the safety, the regulatory compliance as well as the technical suitability of the product for the intended application. The product is not intended for use in medical devices and pharmaceutical applications; Versalis declines all responsibility and cannot be held liable in case of use in the above mentioned applications.
