

Data sheet**HDPE reprocessed black
RSH HDPE 5010 E**

Properties	Test Method	Test Condition	Unit	Value ¹
MFR (Melt Flow Rate)	ISO 1133	190°/5,0 kg	g/10 min	0,5 - 1,0
MVR (Melt Volume Rate)	ISO 1133	190°/5,0 kg	cm ³ /10 min	0,6 - 1,4
Density	ISO 1183	23 ° C	g/cm ³	0,960
Moisture content	Thermo- gravimetric	KERN MLS	%	< 0,2

¹ The information submitted is based on our current experience and knowledge. These data do not release processors from the responsibility of carrying out own tests, neither do they imply any legally binding assurance of certain properties or of the suitability for specific purposes.