

## REPSOL ISPLEN PP040C1E

The grade REPSOL ISPLEN PP040C1E is a phthalate free polypropylene homopolymer specially formulated and adapted for extrusion processes and particularly in thermoforming due to its good transparency and excellent stiffness. It is nucleated and the properties remain even at high regrind fractions. This makes the grade recommendable in barrier sheet packing application.

### Applications

In extrusion processes such as:

- Mainly in sheet extrusion and thermoforming.
- Coextrusion in rigid packaging.
- Others are monofilament and weaving tapes

Recommended melt temperature range from 190 to 250°C. Processing conditions should be optimised for each production line.

PROPERTIES	VALUE	UNIT	TEST METHOD
<b>GENERAL</b>			
Melt flow rate (230°C/ 2,16 kg)	3	g/10 min	ISO 1133
Density at 23°C	905	kg/m <sup>3</sup>	ISO 1183
<b>MECHANICAL</b>			
Flexural Modulus	2000	MPa	ISO 178
Tensile strength at yield	38	MPa	ISO 527-2
Charpy impact strength (23°C, notched)	4	kJ/m <sup>2</sup>	ISO 179
<b>THERMAL</b>			
Vicat softening temperature A120 (10 N)	153	°C	ISO 306
HDT 0.45MPa	105	°C	ISO 75
<b>OTHERS</b>			
Haze (1 mm)	34	%	ASTM D 1003

### Storage

REPSOL ISPLEN PP040C1E should be stored in a dry atmosphere, on a paved, drained and not flooded area, at temperatures under 60°C and protected from UV radiation. Storage under inappropriate conditions could initiate degradation processes or undesired migration of additives included in its formulation which may have a negative influence on the processability and properties of the transformed product.

[1/2]

### Disclaimer

This grade complies with the European regulations for materials for use in food contact. This grade is not intended to be used in medical, pharmaceutical, or healthcare applications, therefore Repsol does not authorize its use in them.

Repsol does not grant express or implicit guarantees that extend beyond the description contained herein. Nothing herein shall constitute any guarantee of merchantability or fitness for a particular purpose. Before using a product sold by Repsol, users must make their own independent determination that the product is safe, legal, and technically suitable for its intended use. Repsol does not assume any responsibility for the use of its materials together with other materials.

### Related documents

The following related documents are available on request, and represent various aspects on the usability and safety of the product:

- Safety data sheet
- Statement on compliance with food contact regulations

**Recommended consumption period:** 12 months from the raw material reception

July 2021

[2/2]