

REPSOL ISPLEN PP087N2M

REPSOL ISPLEN PP087N2M is a phthalate free homopolymer grade with a high fluidity intended for injection moulding. It is characterised by good flow properties that enables to fill the mould easier and by short cycle times in large items and also outstanding organoleptic properties. Articles manufactured with this grade have excellent chemical resistance, are easily decorated and can accept different colouring systems.

Applications

REPSOL ISPLEN PP087N2M is widely used for the production of consumer goods such as:

- Food containers and rigid packaging.
- Vacuum and cosmetic flasks.
- Garden and domestic furniture
- Caps and closures

Recommended melt temperature range from 190 to 250°C. Processing conditions should be optimised for each production line.

PROPERTIES	VALUE	UNIT	TEST METHOD
GENERAL			
Melt flow rate (230°C/ 2,16 kg)	25	g/10 min	ISO 1133
Density at 23°C	905	kg/m ³	ISO 1183
MECHANICAL			
Flexural Modulus	1.900	MPa	ISO 178
Charpy impact strength (23°C, notched)	3	kJ/m ²	ISO 179
THERMAL			
HDT 0.45MPa	100	°C	ISO 75

Storage

REPSOL ISPLEN PP087N2M should be stored in a dry atmosphere, on a paved, drained and not flooded area, at temperatures under 60°C and protected from UV radiation. Storage under inappropriate conditions could initiate degradation processes or undesired migration of additives included in its formulation which may have a negative influence on the processability and properties of the transformed product.

Disclaimer

[1/2]

Technical Data Sheet

Chemicals



This grade complies with the European regulations for materials for use in food contact. This grade is not intended to be used in medical, pharmaceutical, or healthcare applications, therefore Repsol does not authorize its use in them.

Repsol does not grant express or implicit guarantees that extend beyond the description contained herein. Nothing herein shall constitute any guarantee of merchantability or fitness for a particular purpose. Before using a product sold by Repsol, users must make their own independent determination that the product is safe, legal, and technically suitable for its intended use. Repsol does not assume any responsibility for the use of its materials together with other materials.

Related documents

The following related documents are available on request, and represent various aspects on the usability and safety of the product:

- Safety data sheet
- Statement on compliance with food contact regulations

Recommended consumption period: 12 months from the raw material reception

July 2021

[2/2]

This information is offered in good faith and meant only as a guide. The transformer or user will be, in each case, responsible for the processing conditions and the final use of the product. Freedom under patents, copyright and registered designs cannot be assumed.

Technical Service and Development:
Repsol Technology Lab
Ctra. de Extremadura A5, Km 18
28931 Móstoles
Tel. +34 91 753 85 00
atd_poliiolefinas@repsol.com

Headquarters
Méndez Álvaro, 44
28045 Madrid
España
www.repsol.com

Customer Care
sacrq@repsol.com

 All our
polyolefins are
recyclable